

PRODUCT DATASHEET

PPC SURECAST 42,5 R CEMENT



PPC

PPC SURECAST 42,5 R CEMENT IS A PREMIUM PORTLAND CEMENT THAT IS IDEAL FOR THE MANUFACTURE OF PRECAST CONCRETE PRODUCTS, STRUCTURAL REINFORCED AND PRESTRESSED CONCRETE, AND ANY OTHER APPLICATION WHERE HIGH EARLY STRENGTH IS REQUIRED.

Product Description

SURECAST is a premium quality cement made from high quality raw materials. Clinker is inter-ground with gypsum to manufacture a premium high early strength cement.

Applications

A high early strength cement for precast concrete products, structural reinforced and prestressed concrete, masonry products, paving, grouts and shotcrete applications.

SURECAST is a tried and tested product that has been engineered to achieve consistent and appropriate performance.

Specification

SURECAST complies with the 42,5 R strength class of SANS 50197-1 for common cements and, depending on source factory, it is identified as:

- Portland cement CEM I 42,5 R
- Portland-limestone cement CEM II/B-L 42,5 R
- Portland-composite cement CEM II/A-M (S,V) 42,5 R

Storage

Cement bags are not weatherproof and should be stored under cover, off the ground, on a raised timber platform or on plastic sheeting to protect against rising dampness. Bags should be stacked to a maximum height of 12 bags or two pallets. Usage of bags should be first in first out.

Handling and Safety

Refer to PPC Safety Data Sheet at www.ppc.africa.

Technical Information

Typical technical data is supplied on the next page. Further technical information can be obtained from the PPC Cement office on (0800) 236 368.

PPC has comprehensively equipped chemical, cement and concrete laboratories and can supply specific information and assistance regarding cement and concrete technology.

Availability

SURECAST is available throughout South Africa, Botswana and Zimbabwe. Please contact your local sales office for further details.

Typical Properties

Chemical Properties	Typical results	SANS 50197-1 requirements
Sulphur trioxide: % by mass	2,0	3,5% maximum
Chlorides: % by mass	≤ 0,01	0,1% maximum

Physical Properties	Typical results	SANS 50197-1 requirements
Setting times: Initial: minutes Final: minutes	180 260	≤ 60 minimum No requirement
Specific Area (Blaine): m ² /kg	400	No requirement
Typical mortar prism results determined in accordance with SANS 50197-1: Compressive strength at 2 days (MPa) Compressive strength at 28 days (MPa)	± 28 ± 50	≤ 20,0 ≤ 42,5 ≤ 62,5
Soundness: Le Chatelier Expansion (mm)	1	10 maximum
Densities: Relative density Bulk density, aerated, kg/m ³ Bulk density, as packed, kg/m ³	3,10 1300 1500	
Approximate Volume: 50 kg bag, ℓ	± 33	

Please contact our sales office if actual figures are required.

CONTACT US:

JOHANNESBURG

Eastgate 20, Corner Crayston Drive and Katherine Street 148, Sandton
Tel: 011 386 9000

GERMISTON

62 Lower Germiston Rd, Heriotdale, Johannesburg South
Tel: 011 626 3150

CAPE TOWN

Corner of Chain Ave & Montague Drive, Montague Gardens, Milnerton
Tel: 021 550 2100

GEORGE

13 Saagmeul Street, George Industrial
Tel: 044 871 3024

PPC BOTSWANA

Plot 22034, Takatokwane Way Gaborone West,
Tel: (267) 390 1553

IMPORTANT NOTE:

The information and/or specifications contained herein are given in good faith as being true and accurate but no liability is accepted by PPC, its employees, distributors, representatives or agents, for any loss or damage, direct or indirect, resulting from using the information, following the specifications or adopting recommendations and/or suggestions as actual conditions of use are beyond its control.

This data sheet was published in August 2018

Visit our website at: www.ppc.africa



PPC